



# FM CARTIERE S.P.A.

DT LCQ 01  
GUIDA RAPIDA  
Rev.: 25  
Del: 28/10/2022

VIA VALSESIA 22 – MOMO(NO) ITALY- Tel: 0321.990100 / Fax: 0321.990152

Web: <http://www.fmcartiere.com>

LABORATORIO C.Q.: FAX 0321.990151 / e-mail: [malanchin@fmcartiere.com](mailto:malanchin@fmcartiere.com)

UFFICIO VENDITE: TEL.0321.990108 / FAX 0321.990150 – e-mail: [salesoffice@fmcartiere.com](mailto:salesoffice@fmcartiere.com)

Azienda dotata di Sistema di Gestione per la Qualità ISO 9001 – ISO 9001 Quality Management System

## SPECIFICHE TECNICHE – GUIDA RAPIDA DI CONSULTAZIONE TECNICAL SPECIFICATIONS – QUICK CONSULTATION GUIDE

Gr/mq	Parametri	Unità di misura	07	017	047	08K	KA
270	Taber long–Stiffness MD	gr.cm	86	86			
	Taber trasv–Stiffness CD	gr.cm	29	29			
	Spessore - Caliper	microns	350	350			
290	Taber long–Stiffness MD	gr.cm	105	105	90	107	121
	Taber trasv–Stiffness CD	gr.cm	38	38	34	42	51
	Spessore - Caliper	microns	380	380	355	380	380
320	Taber long–Stiffness MD	gr.cm	138	138	120	141	167
	Taber trasv–Stiffness CD	gr.cm	52	52	42	57	65
	Spessore - Caliper	microns	420	420	395	420	425
350	Taber long–Stiffness MD	gr.cm	180	180	165	184	207
	Taber trasv–Stiffness CD	gr.cm	66	66	62	73	86
	Spessore - Caliper	microns	460	460	440	460	460
385	Taber long–Stiffness MD	gr.cm	230	230	225	235	258
	Taber trasv–Stiffness CD	gr.cm	90	90	86	99	110
	Spessore - Caliper	microns	510	510	490	510	510
400	Taber long–Stiffness MD	gr.cm	260	260	245	265	279
	Taber trasv–Stiffness CD	gr.cm	105	105	90	116	121
	Spessore - Caliper	microns	530	530	510	530	530
435	Taber long–Stiffness MD	gr.cm	315	315	305	321	333
	Taber trasv–Stiffness CD	gr.cm	135	135	115	149	154
	Spessore - Caliper	microns	575	575	555	575	575
450	Taber long–Stiffness MD	gr.cm	340	340	325	347	374
	Taber trasv–Stiffness CD	gr.cm	140	140	138	154	165
	Spessore - Caliper	microns	600	600	580	600	600
500	Taber long–Stiffness MD	gr.cm	415	415	405	423	475
	Taber trasv–Stiffness CD	gr.cm	180	180	175	198	209
	Spessore - Caliper	microns	665	665	640	665	670
530	Taber long–Stiffness MD	gr.cm				520	
	Taber trasv–Stiffness CD	gr.cm				264	
	Spessore - Caliper	microns				700	
550	Taber long–Stiffness MD	gr.cm	540	540	520		591
	Taber trasv–Stiffness CD	gr.cm	250	250	240		286
	Spessore - Caliper	microns	720	720	700		730

**Prodotti certificati FSC® disponibili su richiesta – FSC® certificated products available on request**

### LEGENDA - KEY:

	CONDIZIONI DI FORNITURA: QUANTITÀ MINIMA PER ORDINE TON.10 + FORMATI AUTOABBINABILI O LUCE MACCHINA SUPPLY CONDITIONS: ORDER MINIMUM QUANTITY TON 10 + SELF COMBINED OR WIDTH MACHINE SIZES
	CARTONCINO RETRO GRIGIO – BOARD GREY BACK
	CARTONCINO RETRO MANILLA – BOARD MANILLA BACK
	CARTONCINO RETRO BIANCO PATINATO – WHITE COATED BACK
	CARTONCINO RETRO KRAFT – KRAFT BACK
	CARTONCINO RETRO KRAFT ALIMENTARE– KRAFT BACK FOR DRY FOOD CONTACT

Laboratorio Controllo Qualità – Quality Control Laboratory:  
Estella Malanchin

*Estella Malanchin*